



FASTSET™
FSD185HT

Product Highlights

- Fast setting polyurethane with exceptional green strength
- Specially formulated to produce parts with a high heat tolerance
- Semi rigid feel with great impact strength
- A 1:1 mix ratio by volume great for meter mix or cartridge gun applications

Mixing Properties:	Resin (Isocyanate) Part A	Hardener (Polyol) Part B
Mix Ratio (Parts by Weight)	100	87
Mix Ratio (Parts by Volume)	100	100
Color	Yellow	Black
Viscosity @ 77F	700	900
Mixed Viscosity @ 77F	900	
Specific Gravity @ 77F (mixed)	1.09	
Gel Time @77F	60 seconds +/- 10 seconds	
Demold Time (varies w/ mass)	30 minutes – 1 hour	

Physical Properties:	ASTM Method	Cure 1
Hardness, Shore D	D-2240	85 +/- 5
Density @ 77°F (g/cc)	D-792	1.09
Flexural Modulus (PSI)	D-790	180,000
Flexural Strength (PSI)	D-790	240,000
Tensile Strength (PSI)	D-638	6,500
Elongation (%)	D-638	8
IZOD Impact Notched (ft-lb/in)	D-256	1.6
Shrinkage (in/in) (5" sample)	D-2566	.003
Heat Deflection Temperature (@ 66 PSI)	D-648	255 F
Color	VISUAL	BLACK

Cure 1: Physical properties obtained using ambient room temperature (77°F). Tested after 7 days

Other related products offered

- Silicone rubber
- Mold release agents
- Mix tubes
- Additional products available. Inquire directly for products not listed.

Processing suggestions:

- Thoroughly agitate polyol (hardener) component to be sure the liquid is homogeneous.
- Properly weigh out the appropriate amounts of resin and hardener.
 - Mix thoroughly being sure to scrape sides and bottom of container.
 - Pressurize mold in a pressure pot at 60psi until cured.

Kit Sizes and Weights:

• Quart Kit	3.7 lbs.
• Gallon Kit	15.0 lbs.
• Five Gallon Kit	74.8 lbs.
• Drum Kit	822.8 lbs.

Safety Precautions:

The safety data sheet (SDS) for this or any Thermoset Solutions, LLC product should be read prior to use and is available upon request from Thermoset Solutions, LLC.

Use in a ventilated area. Avoid contact with skin using protective gloves and protective clothing. Repeated or prolonged contact on the skin may cause an allergic reaction. Eye protection is extremely important. Always use approved safety glasses or goggles when handling this product.

If Contact Occurs:

- Eyes: Immediately flush with water for at least 15 minutes. Call a physician.
- Skin: Immediately wash with soap and water. Remove contaminated clothing. Do not use solvents to wash skin. Seek medical attention if allergic reaction occurs.
- Ingestion: If swallowed, call a physician immediately. Remove stomach contents by gastric suction or induce vomiting only as directed by medical personnel.

Notice:

The information contained in this tech data sheet is considered accurate. However, no warranty is expressed or implied regarding the accuracy of the data, the results to be obtained from the use thereof, or that any such use will not infringe upon a patent. User shall determine the suitability of the product for the intended application and assume all risk and liability whatsoever in connection therewith.