

Product Highlights

- Specifically formulated for extreme handholds in the climbing wall industry
- Fast setting polyurethane with exceptional green strength
- Specially formulated to produce low color parts with UV resistance
- Semi rigid feel with great impact strength
- A 1:1 mix ratio by volume great for meter mix or cartridge gun applications

Mixing Properties:	Resin (Isocyanate) Part A	Hardener (Polyol) Part B
Mix Ratio (Parts by Weight)	100	90
Mix Ratio (Parts by Volume)	100	100
Color	Yellow	Translucent
Viscosity @ 77F	330	550
Mixed Viscosity @ 77F	400	
Specific Gravity @ 77F (mixed)	1.11	
Gel Time @77F	2 min	
Demold Time (varies w/ mass)	15 - 20 min	

Physical Properties:	ASTM Method	Cure 1
Hardness, Shore D	D-2240	73D
Density @ 77°F (g/cc)	D-792	1.09
Flexural Modulus (PSI)	D-790	215,000
Tensile Strength (PSI)	D-638	4100
Elongation (%)	D-638	35
IZOD Impact Notched (ft-lb/in)	D-256	2.0
Shrinkage (in/in) (5" sample)	D-2566	.004
Heat Deflection Temperature (@ 66 PSI)	D-648	130 F
Color	VISUAL	Translucent

Cure 1: Physical properties obtained using ambient room temperature (77°F). Tested after 7 days

Other related products offered

- Silicone rubber
- Mold release agents
- Mix tubes
- Additional products available. Inquire directly for products not listed.

Processing suggestions:

- Thoroughly agitate both components separately to be sure the liquid is homogeneous.
- For best results, material should be processed above 65F.
- If hand mixing, properly weigh out the appropriate amounts of resin and hardener.
 - Mix thoroughly being sure to scrape sides and bottom of container.
 - For best results, de-air the product before pouring into mold.
 - Pressurize mold in a pressure pot at 60psi until cured.
 - Mold temperature is recommended to be 150 °F for faster de-mold, otherwise longer time in room temperature mold will be required.

Kit Sizes and Weights:

- | | |
|-------------------|-----------|
| • Quart Kit | 3.8 lbs. |
| • Gallon Kit | 15.2 lbs. |
| • Five Gallon Kit | 76 lbs. |
| • Drum Kit | 855 lbs. |

Safety Precautions:

The safety data sheet (SDS) for this or any Thermoset Solutions, LLC product should be read prior to use and is available upon request from Thermoset Solutions, LLC.

Use in a ventilated area. Avoid contact with skin using protective gloves and protective clothing. Repeated or prolonged contact on the skin may cause an allergic reaction. Eye protection is extremely important. Always use approved safety glasses or goggles when handling this product.

If Contact Occurs:

- Eyes: Immediately flush with water for at least 15 minutes. Call a physician
- Skin: Immediately wash with soap and water. Remove contaminated clothing. Do not use solvents to wash skin. Seek medical attention if allergic reaction occurs.
- Ingestion: If swallowed, call a physician immediately. Remove stomach contents by gastric suction or induce vomiting only as directed by medical personnel.

Notice:

The information contained in this tech data sheet is considered accurate. However, no warranty is expressed or implied regarding the accuracy of the data, the results to be obtained from the use thereof, or that any such use will not infringe upon a patent. User shall determine the suitability of the product for the intended application and assume all risk and liability whatsoever in connection therewith.